

**PRODUCT NAME:** 3D FILAMENT PVA-2 1,75mm

**PRODUCT DESCRIPTION:** PVA-2 filament is a poly(vinyl alcohol) in the form of a thread, designed for 3D printing using the FFF/FDM method. Filament coiled on spools, vacuum-packed with desiccant in a PET/PE bag, and then in a box.

**STORAGE:** Store in dry area. Store in a closed container.

## PRODUCT PARAMETERS

Parameter	Value
Filament diameter [mm]	1,75
Diameter tolerance [mm]	+/- 0,05
Oval tolerance [mm]	+/- 0,02
Net weight [g]	<b>500</b>
Weight with packaging [g]	900
Spool weight [g]	Transparent PC: 245
	ECO PP wood: 190
Spool dimensions [mm] (ø / height / hole ø)	Transp. PC: 200/55/52
	ECO PP wood: 200/57/52
Box dimensions [mm]	220/210/65

## RECOMMENDED PRINTING PARAMETERS

Parameter	Value
Print temperature [°C]	190-215
Bed temperature [°C]	50-70
Cooling [%]	50-100
Closed chamber	Not necessary
<b>We recommend that drying the filament before printing at 45°C for at least 4h</b>	

## PHYSICAL PARAMETERS OF THE MATERIAL

Parameter	Value	Unit	Test method
Density	1,25	g/cm <sup>3</sup>	ISO 1183
Max. moisture absorption from air at 23°C and 50% relative humidity	~4	%	-
Melting point	180-190	°C	-
Glass transition temperature	60-65	°C	-
Water solubility	YES	-	-
Biodegradability „OK biodegradable water”	YES	-	ISO 14851
Toxicity	NO	-	-

The values above have been measured using standard test specimens made of non-colored material at room temperature. The figures should be considered as indicative values only. Actual properties of PVA-2 parts can be affected by the printing parameters, design of the model, ambient conditions, application of the printout etc. It is essential that users test our products to determine whether they are suitable for their intended use. ROSA PLAST Sp. z o.o. accepts no liability for any health detriment or material losses or any other losses related to the use of the material.

